

FULLBACK®FC PREMIUM SIDING INSULATION FOR FIBER CEMENT

PRODUCT DATA SHEET

This is graphite enhanced expanded polystyrene (EPS) insulation made with BASF's patented Neopor® bead.



SPECIFICATIONS AND PERFORMANCE

Dimensions	.63" Base Thickness	1.0" Base Thickness	1.1" Base Thickness
48" x 44" For use with 4" exposure (5-1/4" plank)	R-3.0 250 Sq. Ft. Per Pkg	R-4.6 161 Sq. Ft. Per Pkg	R-5.0 147 Sq. Ft. Per Pkg
48" x 45" For use with 5" exposure (6-1/4" plank)	R-3.0 255 Sq. Ft. Per Pkg	R-4.6 165 Sq. Ft. Per Pkg	R-5.0 150 Sq. Ft. Per Pkg
48" x 48" For use with 6" exposure (7-1/4" plank)	R-3.0 272 Sq. Ft. Per Pkg	R-4.6 176 Sq. Ft. Per Pkg	R-5.0 160 Sq. Ft. Per Pkg
48" x 42" For use with 7" exposure (8-1/4" plank)	R-3.0 238 Sq. Ft. Per Pkg	R-4.6 154 Sq. Ft. Per Pkg	R-5.0 140 Sq. Ft. Per Pkg
48" x 48" For use with 8" exposure (9-1/4" plank)	R-3.0 272 Sq. Ft. Per Pkg	R-4.6 176 Sq. Ft. Per Pkg	R-5.0 160 Sq. Ft. Per Pkg

Physical Property	ASTM Method	Performance
Classification of Insulation	ASTM C578	Type I
Density lb./ft ³ (kg/m ³)	ASTM D1622	Minimum .90
Water Vapor Permeance of 1.00 in thickness, Min, perm (ng/Pa•s•m ²)	ASTM E96	up to 3.5
Compressive Strength, PSI (kPa)	ASTM D1621	Minimum 10
Flexural Strength, PSI (kPa)	C203	Minimum 25
Surface Burning Characteristics: Flame Spread Smoke Developed	ASTM E84 / UL 723	<25 <450

Read This Before You Buy - What You Should Know About R-values

The chart shows the R-value of this insulation. R means resistance to heat flow. The higher the R-value, the greater the insulating power. Compare insulation R-values before you buy. There are other factors to consider. The amount of insulation you need depends mainly on the climate you live in. Also, your fuel savings from insulation will depend upon the climate, the type and size of your house, the amount of insulation already in your house, and your fuel use patterns and family size. If you buy too much insulation, it will cost you more than what you'll save on fuel. To get the marked R-value, it is essential that this insulation be installed properly.

Additional Information

BASF's Neopor has been qualified in accordance with the ICC-ES (International Code Council) Acceptance Criteria for Foam Plastic Insulation (AC12). Tiny graphite particles give Neopor its silver/gray color and provide up to 20% more insulation value than traditional expanded polystyrene insulation.

Fullback®FC is treated with PREVENTOL®TM EPS, a systemic insecticide which protects the foam from termite damage. The active ingredient in PREVENTOL®TM EPS is used in low concentrations and is safe for installers and homeowners.

Progressive Foam's manufacturing process includes a combination of heat and pressure, utilizing clean technologies that minimize energy and water inputs through closed loop energy recycling. No solid waste is generated in production, and no generated waste goes to the landfill. All waste is fully recaptured and repurposed.

Neopor® is treated with a flame retardant; however, all foam plastic insulation will ignite if exposed to fire of sufficient heat and intensity. Protect foam insulation from exposure to open flame or other ignition sources during shipment, storage, and installation.

Prolonged exposure to ultraviolet radiation may cause the surface of the insulation to degrade. A light-colored, opaque protective covering should be used if excessive solar exposure is expected.



Disclaimer

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Progressive Foam Technologies, Inc. makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation.



Progressive Foam Technologies, Inc. • 6753 Chestnut Ridge Road Beach City, Ohio 44608 • 1-800-860-3626
For the most current version of our literature, visit www.progressivefoam.com