


PROBOARD® VERSA™ VP PREMIUM GPS

Vapor-Permeable Rigid Insulation

Made with high-performance Graphite Polystyrene (GPS)

TECHNICAL DATA SHEET



SPECIFICATIONS AND PERFORMANCE

| Product Details | Test Method | Performance | |
|---|-------------|--------------------------------|---------|
| Compressive Strength, PSI (kPa) [min] [results based on 1" thickness] | ASTM D1621 | 10 | 15 |
| Thickness | - | varies* | |
| R-Value, 75° F (Btu • in. / ft. ² hr • F°) [per nominal inch] | ASTM C518 | 5.0** | |
| Dimensions, width x length [ft.] | - | 4x8, 4x9 | |
| Component Properties | Test Method | Performance | |
| Film Type | - | flexible plastic, metalized*** | |
| Film Thickness [nominal mil] | - | 1.5, 1.0 | |
| Physical Properties of the GPS | Test Method | Performance | |
| Classification of Insulation Component | ASTM C578 | Type I | Type II |
| Density lb./ft ³ (kg/m ³) [min] | ASTM D1622 | 0.90 | 1.35 |
| Water Absorption by Total Immersion [max, volume %] | ASTM C272 | 4.0 | 3.0 |
| Flexural Strength, PSI (kPa) [min] [results based on 1" thickness] | ASTM C203 | 25 | 35 |
| Composite Properties | Test Method | Performance | |
| Water Vapor Permeance [varies based on thickness and Type] | ASTM E96 | 1.0 - 5.0 | |
| Vapor Retarder Classification | ASTM E96 | Class III | |
| Water Penetration of Exterior...by Uniform Static Air Pressure Difference | ASTM E331 | Pass | |
| Surface Burning Characteristics: Flame Spread Smoke Developed | UL 723 | 5 25 | |

* .59", .75", 1.02", 1.55", 2.09"

**Nominal inch is 1.0625"

***For thicknesses above 2.50", flexible plastic/flexible plastic films are used [1.5mil]



Read This Before You Buy - What You Should Know About R-values

The chart shows the R-value of this insulation. R means resistance to heat flow. The higher the R-value, the greater the insulating power. Compare insulation R-values before you buy. There are other factors to consider. The amount of insulation you need depends mainly on the climate you live in. Also, your fuel savings from insulation will depend upon the climate, the type and size of your house, the amount of insulation already in your house, and your fuel use patterns and family size. If you buy too much insulation, it will cost you more than what you'll save on fuel. To get the marked R-value, it is essential that this insulation be installed properly.

Additional Information

Treated with PREVENTOL®TM EPS, a systemic insecticide which protects the foam from termite damage. The active ingredient in PREVENTOL®TM EPS is used in low concentrations and is safe for installers and homeowners.

Progressive Foam's manufacturing process includes a combination of heat and pressure, utilizing clean technologies that minimize energy and water inputs through closed loop energy recycling. No solid waste is generated in production, and no generated waste goes to the landfill. All waste is fully recaptured and repurposed.

Treated with a flame retardant; however, all foam plastic insulation will ignite if exposed to fire of sufficient heat and intensity. Protect foam insulation from exposure to open flame or other ignition sources during shipment, storage, and installation.

Prolonged exposure to ultraviolet radiation may cause the surface of the insulation to degrade. A light-colored, opaque protective covering should be used if excessive solar exposure is expected.

Meets IECC 2009, 2012, 2015, 2018, 2021 and 2024 Residential and Commercial Energy Code for Exterior Continuous Insulation Sheathing.

UL* Certified Safety US R18532

UL Solutions Evaluations Service Report: UL ER 18532

Foam Plastic Sheathing Panels Used as Water-resistive Barriers [WRB] - Compliant for products 0.50" and thicker when using an AMMA 711 or AC148 tested tape at joints, seams, and penetrations. Penetrations only can be sealed with approved AMMA 713 caulks and sealants.

Disclaimer

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Progressive Foam Technologies, Inc. makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation.